

# Capadecor® Stucco Eleganza

Synthetic resin filling compound to obtain sheeny surfaces with metallike characteristics.



## Product Description

Field of Application

Tintable, silk-gloss synthetic resin dispersion for the decorative design of interior walls.

Material Properties

- Easy to apply.
- Characteristic definition.
- Efficient and safe processing technology.

Packaging/Package Size

- 2.5 litres

Colours

Creme white, metallic

**Tinting:**

The product is tintable via ColorExpress in numerous colours of the Caparol 3D System PLUS.

**Stir up tinted product very thoroughly before applying.**

The product typical definition (surface appearance) is highly depending on selected colour shade and processing technology.

When applying on seamless surfaces, all tinted product must be thoroughly mixed before use to avoid colour differences.

Gloss Level

Satin-/Silk-gloss (mid sheen)

Storage

Store in a cool, but frost-free place.

Technical Data

- Density: Approx. 1.2 g/ml

Supplementary Product

- AkkordSpachtel fein (fine filler)
- Capadecor DecoGrund

Suitability according to  
Technical Information No. 606  
Definition of Application Areas

| Interior 1   | Interior 2 | Interior 3 | Exterior 1 | Exterior 2 |
|--|------------|------------|------------|------------|
| +  | +          | ○          | -          | -          |
| (-) inapplicable / (○) of limited suitability / (+) suitable |            |            |            |            |



## Application

|                        |   |
|------------------------|---|
| Suitable Substrates    | <p>Interior surfaces: Mineral plasters in mortar groups PII (lime-cement mortars), PIII (cement mortars), PIV (gypsum mortar and ready-mixed gypsum plaster), plasterboards, gypsum wallboards and concrete.</p> <p>The substrate must be dry, clean, sound/stable, planar (trowelled up smoothly), without any colour contrast, and free from all substances that may prevent good adhesion.<br/>In Germany: Follow VOB, part C, DIN 18363, section 3.</p> <p>Follow Technical Information No. 650 for substrate preparation.</p>  |
| Substrate Preparation  | <p>Coarse (roughly textured) substrates, walls made of plasterboards and all walls and ceilings subjected to adverse lighting conditions (sided/grazing light) should be prepared to match quality level Q4.</p> <p>Intermediate sanding after drying of filler coat (up to P200-240 grit). Then prime with CapaSol in order to equalize the absorption capacity and for embedding dust particles</p> <p>Substrates of approximately quality level Q4 can directly be coated with Capadecor DecoGrund, as described (see "Priming Coat:").</p>  |
| Method of Application  | <p><b>Priming Coat:</b><br/>Roller-apply one priming coat of Capadecor DecoGrund, tinted to match the finishing coat in shade, then smoothen with a Venetian trowel, avoiding deeper trowel marks or burrs.</p> <p><b>Intermediate Coat:</b><br/>On large, seamless surfaces: Apply Stucco Eleganza wet-on-wet with a Venetian trowel, thus avoiding prematurely drying.<br/>Providing that min. 2 hands are on the job, apply Stucco Eleganza using a short pile roller and then smoothen with a Venetian trowel. Therefore apply such an amount of product that the surface can be smoothened before it begins to set.</p> <p><b>Finishing Coat:</b><br/>The finishing coat is effected in the same way as described above for intermediate coat, but due to individual working methods, the final work step should always be carried out by only one skilled worker per surface.</p> |
| Thinning               | Apply Stucco Eleganza always undiluted.   |
| Consumption            | Approx. 50 - 70 ml/m <sup>2</sup> per coat (work step). Determine the exact amount of material required by coating a test area on site.   |
| Application Conditions | <b>Low Temperature Limit for Application and Drying:</b><br>+5 °C for product, ambient air and substrate.   |
| Drying/Drying Time     | At + 20 °C and 65 % relative humidity surface-dry after 30 - 60 minutes. Completely cured and ready for stress after 1 - 2 days. Lower temperatures and higher relative humidity extend the drying time.  |
| Tools                  | For applying Stucco Eleganza the use of a short pile roller (10 - 12 mm piles) and abrasion-resistant Venetian trowel is advisable. Before doing so, generally smooth the trowel with wet abrasive paper (400 - 600 grit) and remove sharp edges.   |
| Tool Cleaning          | Immediately after use with soapy water.   |
| Note                   | <b>Advice for Cleaning and Care:</b><br>Always check for cleanability, previously by trials (test area), working with due care. Note: Changes in surface appearance, caused by cleaning, are <u>not</u> removable.<br>Depending on the colour shade of coating, the surface of Stucco Eleganza may show minor scratch marks, when being stressed (low "writing resistance").  |

## Advice

|  |  |
|--|--|
| Please Note (Status as at Date of Publication) | <p>Keep out of reach of children. Ensure good ventilation during use and drying. Do not eat, drink or smoke while using the product. In case of contact with eyes or skin, immediately and thoroughly rinse with water. Do not allow product to enter drains, waterways or soil. Clean utensils immediately after use with soap and water. Do not breathe spray dust. Use A2/P2 combination filter for paint spraying. Further information: See Material Safety Data Sheet (MSDS).</p> <p>Contains 2-methyl-2H-isothiazol-3-one. May produce an allergic reaction.<br/>In Germany: Advice for allergy sufferers with isothiazolinone allergy: Hotline 0180/5308928 (0.14 €/minute from German landline, MTS max. 0.42 €/minute).</p> |
| Disposal                                       | <p>Materials and all related packaging must be disposed of in a safe way in accordance with the full requirements of the local authorities. Particular attention should be made to removing wastage from site in compliance with standard construction site procedures.</p> <p>In Germany: Only completely empty containers should be handed in for recycling. Dispose containers with residues of liquid material as remnants of water-based paints and dried material as hardened paints waste or via domestic waste.</p>  |
| Giscode  | M-DF02 (Germany)   |

Substances of Content - Declaration

Blend of acrylate/vinyl acetate polymers, mineral fillers, water, additives, preservative (methylisothiazolinone).

Technical Assistance

As it is impossible to list herein the wide variety of substrates and their specific problems, please request our technical assistance in case of queries. We will describe appropriate working methods, if a substrate not specified above is to be coated.

Customer Service Centre

Tel.: +49 06154- 71 7 1710  
Fax: +49 05154- 71 7 1711  
e-mail: kundenservicecenter@caparol.de

International Distribution: Please see [www.caparol.com](http://www.caparol.com)

## Technical Information No.914 · Issue: July 2016

All suggestions and application instructions herein are based on our latest technical experience. Due to the wide variety of individual project conditions, we cannot be held responsible for their content. These instructions do not release the purchaser/ applicator from his responsibility to determine the suitability of the product in consideration of the project characteristics. These instructions are to be considered void when a new edition is released. Our general conditions of sale and delivery in their latest edition apply. This document is a translation of our German Technical Information No.914 · Capadecor®  
Stucco Eleganza · Issued: February 2016